

FRAMECAD Heterogenous Vinyl Flooring

Heterogenous PVC Flooring, with Poly-urethane reinforced base layer, printed decorative layer, and wear resistant clear top layer

Applications

- Homes and Villa's
- Shopping Centres
- Retirement Centres
- Offices
- Auditoriums

Features & Benefits

- Real life wood patterns with realistic embossed surface finish
- Durable and wear resistant surface
- No wax or polish required
- High Anti-slip rating
- Available in Rolls or Tiles 610mm x 610mm

Environmental Info

- Manufactured according to ISO14001:2004 environmental standard

Manufacturing Classification:

- Manufactured under an ISO9001:2001 certified quality management system
















Installation:

- Colour matched welding rods available
- For detailed installation instructions, please contact info@framecad.com

SPECIFICATIONS					
	Total Thickness (mm)	Roll Width (m)	Roll Length (m)	Area per 20' GP	Wear Layer
FRAMECAD Heterogenous Vinyl Flooring	2.0	2.0	15.0	6,500	0.50
	2.0	2.0	15.0	6,500	0.70
	3.0	2.0	15.0	6,500	0.20
	3.0	2.0	15.0	6,500	0.30
	3.0	2.0	15.0	6,500	0.50

PERFORMANCE		
Weight	EN 430	2.0mm: 3.50 kg/m ² (max) 3.0mm: 5.25 kg/m ² (max)
Reaction to Fire	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2 ASTM E648-06	Class Bfl-S1 ≥ 8 kw/m ² Pass Type I
Flexibility	EN 435 ASTM F137	< 20mm Pass
Slip Resistance	EN 13893 DIN 51130	Class DS R9
Abrasion Resistance	EN 660-2 ASTM D3384	Wear Group T Pass
Residual Indentation	EN 433 ASTM F970 ASTM F1914	< 0.1mm Pass Pass
Castor Chair	EN 425	Continuous Use
Light Fastness	EN 20105: B02 ASTM F1515	> Blue Wool Standard 6 Pass
Wear Layer Thickness	EN 429 ASTM F410	0.50mm, 0.70mm Pass
Electrical Behaviour (Body Voltage)	EN 1815	< 2.0kV
Dimensional Stability	EN 434	< 0.4mm
Stain and Chemical Resistance	EN 423 ASTM F925	Good Resistance Pass
Thermal Resistance	ISO 8302 (EN 12664) ASTM 1514	< 0.00752m ² K/W Pass
Smoke Density	ASTM E 662-05	< 450
Fungi and Bacteria Resistance		Does not favour growth

FRAMECAD Heterogenous Vinyl Flooring



FRAMECAD Cladding and Lining is distributed by:
FRAMECAD Building Products
PO Box 1292
Auckland 1140, New Zealand

P +64 9 377 6640
F +64 9 307 7139
E info@framecad.com

Innovation Integration Sustainability

www.framecad.com