

Villaboard®

A high performance internal lining that has been especially developed for wet and dry areas and wherever high impact resistance is needed.

Applications

- Ideal for use in high wear areas or wherever durability and fire resistance is critical.
- Suitable for use in residential and commercial applications.

Features & Benefits

- FRAMECAD Villaboard® is resistant to permanent damage from moisture and rotting when installed and maintained correctly. Tested in accordance with AS/NZS2908.2.
- Non combustible and resists flame spread. Fire ratings up to 60mins can be achieved with FRAMECAD Villaboard® - technical details available on request.
- Coated with an enhanced primer which means better adhesion with tile and wallpaper adhesives and less paint required for painted finishes.
- Good flexural strength, meaning it can be easily transported and handled without cracking.
- High impact strength means less rework caused by damage during the construction process.

Environmental Info

- The raw materials used to manufacture fibre cement are low in toxicity - wood pulp, cement, sand and water (recycled up to 4 times).
- Fibre cement is non-toxic to dispose of.
- H&S - Fibre cement is inert, non-toxic and not prone to off-gassing of volatile materials.

Manufacturing Classification

- FRAMECAD Villaboard® sheets are manufactured to AS/NZS 2908.2 'Cellulose - Cement Products Part 2: Flat Sheets' (ISO 8336 'Fibre Cement Flat Sheets').
- ISO9001 'Telarc' certified manufacturer.



Villaboard®

SPECIFICATIONS							
	Thickness (mm)	Profile	Length (mm)	Width (mm)	Area per Sheet (sqm)	Weight per Sheet (kg)	Units per pack
Villaboard® Sheet	6mm	Rec 2 Sides	3000	1200	3.6	29.9	20
		Rec 2 Sides	2700	1200	3.24	26.7	20
		Rec 2 Sides	2400	1200	2.88	23.9	20
		Rec 4 Sides	2400	1200	2.88	23.9	20
		Rec 4 Sides	3000	1200	3.6	29.9	20
		Rec 4 Sides	2400	1200	2.88	23.9	20
	9mm	Rec 2 Sides	3000	1200	3.6	44.6	20
		Rec 2 Sides	2700	1200	3.24	40.2	20
		Rec 2 Sides	2400	1200	2.88	35.7	20
		Rec 4 Sides	2400	1200	2.88	35.7	20
		Rec 4 Sides	3000	1200	3.6	44.6	20
		Rec 4 Sides	2400	1200	2.88	35.7	20

EARLY FIRE HAZARD INDICES – TESTED TO AS 1530 PART 3	
Ignition Index	0
Flame Spread Index	0
Heat Evolved Index	0
Smoke Developed Index	0-1

FRAMECAD Cladding & Lining
is distributed by:
Bon Pacific Trading Limited
PO Box 1292
Auckland 1140, New Zealand

P +64 9 377 6640
F +64 9 307 7139
E info@bonpac.com
www.bonpac.com

Innovation Integration Sustainability
www.framecad.com